

WHAT IS CLAIMED IS:

1 1. A use of a photocurable preceramic polymer to fabricate
2 a silicon carbide containing ceramic or ceramic composite
3 for the application of diesel particulate filters.
4

5 2. A use of a photocurable preceramic polymer to fabricate
6 a silicon carbide containing ceramic or ceramic composite
7 which is microwave susceptible.
8

9 3. A use of a photocurable preceramic polymer to fabricate
10 a microwave susceptible silicon carbide containing ceramic
11 or ceramic composite for the application of regenerative
12 diesel particulate filters.
13

14 4. A use of a photocurable preceramic polymer to fabricate
15 a microwave susceptible silicon carbide containing ceramic
16 or ceramic composite for the application of regenerative
17 diesel particulate filters composed of matted ceramic

1 fibrils shaped in a corrugated cylindrical geometry.

2

3 5. A use of a photocurable preceramic polymer to fabricate
4 a microwave susceptible silicon carbide containing ceramic
5 or ceramic composite for the application of regenerative
6 diesel particulate filters composed of matted ceramic
7 fibrils shaped in a conical geometry.

8

9 6. A use of a photocurable preceramic polymer to fabricate
10 a silicon carbide containing ceramic or ceramic composite
11 for the applications of radiant burners, thermal oxidizers
12 of volatile organic compounds, filters, and automotive
13 catalytic converters.

14

15 7. A use of a photocurable preceramic polymer to fabricate
16 a boron carbide containing ceramic or ceramic composite for
17 the application of diesel particulate filters.

18

1 8. A use of a photocurable preceramic polymer to fabricate
2 a boron carbide containing ceramic or ceramic composite
3 which is microwave susceptible.
4

5 9. The use of a photocurable preceramic polymer to
6 fabricate a microwave susceptible boron carbide containing
7 ceramic or ceramic composite for the application of
8 regenerative diesel particulate filters.
9

10 10. A use of a photocurable preceramic polymer to fabricate
11 a microwave susceptible boron carbide containing ceramic or
12 ceramic composite for the application of regenerative diesel
13 particulate filters composed of matted ceramic fibrils
14 shaped in a corrugated cylindrical geometry.
15

16 11. The use of a photocurable preceramic polymer to
17 fabricate a microwave susceptible boron carbide containing
18 ceramic or ceramic composite for the application of

1 regenerative diesel particulate filters composed of matted
2 ceramic fibrils shaped in a conical geometry.

3

4 12. A use of a photocurable preceramic polymer to fabricate
5 a boron carbide containing ceramic or ceramic composite for
6 the applications of radiant burners, thermal oxidizers of
7 volatile organic compounds, filters, and automotive
8 catalytic converters.

9

10 13. A use of a photocurable preceramic polymer to fabricate
11 a lithium aluminosilicate containing ceramic or ceramic
12 composite for the application of diesel particulate filters.

13

14 14. A use of a photocurable preceramic polymer to fabricate
15 a lithium aluminosilicate containing ceramic or ceramic
16 composite which is microwave susceptible.

17

18 15. A use of a photocurable preceramic polymer to fabricate

1 a microwave susceptible lithium aluminosilicate containing
2 ceramic or ceramic composite for the application of
3 regenerative diesel particulate filters.
4

5 16. A use of a photocurable preceramic polymer to fabricate
6 a microwave susceptible lithium aluminosilicate containing
7 ceramic or ceramic composite for the application of
8 regenerative diesel particulate filters composed of matted
9 ceramic fibrils shaped in a corrugated cylindrical geometry.
10

11 17. The use of a photocurable preceramic polymer to
12 fabricate a microwave susceptible lithium aluminosilicate
13 containing ceramic or ceramic composite for the application
14 of regenerative diesel particulate filters composed of
15 matted ceramic fibrils shaped in a conical geometry.
16

17 18. A use of a photocurable preceramic polymer to fabricate
18 lithium aluminosilicate containing ceramic or ceramic

1 composite for the applications of radiant burners, thermal
2 oxidizers of volatile organic compounds (VOCs), filters, and
3 automotive catalytic converters..
4

5 19. A use of a photocurable preceramic polymer to fabricate
6 a silicon nitride containing ceramic or ceramic composite
7 for the application of diesel particulate filters.
8

9 20. A use of a photocurable preceramic polymer to
10 fabricate a silicon nitride containing ceramic or ceramic
11 composite which is microwave susceptible.
12

13 21. The use of a photocurable preceramic polymer to
14 fabricate a microwave susceptible silicon nitride containing
15 ceramic or ceramic composite for the application of
16 regenerative diesel particulate filters.
17

18 22. A use of a photocurable preceramic polymer to fabricate

1 a microwave susceptible silicon nitride containing ceramic
2 or ceramic composite for the application of regenerative
3 diesel particulate filters composed of matted ceramic
4 fibrils shaped in a corrugated cylindrical geometry.
5

6 23. A use of a photocurable preceramic polymer to fabricate
7 a microwave susceptible silicon nitride containing ceramic
8 or ceramic composite for the application of regenerative
9 diesel particulate filters composed of matted ceramic
10 fibrils shaped in a conical geometry.
11

12 24. A use of a photocurable preceramic polymer to fabricate
13 a silicon nitride containing ceramic or ceramic composite
14 for the applications of radiant burners, thermal oxidizers
15 of volatile organic compounds (VOCs), filters, and
16 automotive catalytic converters.
17

18 25. A use of a preceramic polymer to fabricate a silicon

1 carbide containing ceramic or ceramic composite for the
2 application of diesel particulate filters.

3

4 26. A use of a preceramic polymer to fabricate a silicon
5 carbide containing ceramic or ceramic composite which is
6 microwave susceptible.

7

8 27. A use of a preceramic polymer to fabricate a microwave
9 susceptible silicon carbide containing ceramic or ceramic
10 composite for the application of regenerative diesel
11 particulate filters.

12

13 28. A use of a preceramic polymer to fabricate a microwave
14 susceptible silicon carbide containing ceramic or ceramic
15 composite for the application of regenerative diesel
16 particulate filters composed of matted ceramic fibrils
17 shaped in a corrugated cylindrical geometry.

18

1 29. The use of a preceramic polymer to fabricate a
2 microwave susceptible silicon carbide containing ceramic or
3 ceramic composite for the application of regenerative diesel
4 particulate filters composed of matted ceramic fibrils
5 shaped in a conical geometry.

6
7 30. A use of a preceramic polymer to fabricate a silicon
8 carbide containing ceramic or ceramic composite for the
9 applications of radiant burners, thermal oxidizers of
10 volatile organic compounds, filters, and automotive
11 catalytic converters.

12
13 31. A use of a preceramic polymer to fabricate a boron
14 carbide containing ceramic or ceramic composite for the
15 application of diesel particulate filters.

16
17 32. A use of a preceramic polymer to fabricate a boron
18 carbide containing ceramic or ceramic composite which is

1 microwave susceptible.

2

3 33. A use of a preceramic polymer to fabricate a microwave
4 susceptible boron carbide containing ceramic or ceramic
5 composite for the application of regenerative diesel
6 particulate filters.

7

8 34. A use of a preceramic polymer to fabricate a microwave
9 susceptible boron carbide containing ceramic or ceramic
10 composite for the application of regenerative diesel
11 particulate filters composed of matted ceramic fibrils
12 shaped in a corrugated cylindrical geometry.

13

14 35. A use of a preceramic polymer to fabricate a microwave
15 susceptible boron carbide containing ceramic or ceramic
16 composite for the application of regenerative diesel
17 particulate filters composed of matted ceramic fibrils
18 shaped in a conical geometry.

1 36. A use of a preceramic polymer to fabricate a boron
2 carbide containing ceramic or ceramic composite for the
3 applications of radiant burners, thermal oxidizers of
4 volatile organic compounds, filters, and automotive
5 catalytic converters.

6

7 37. A use of a preceramic polymer to fabricate a lithium
8 aluminosilicate containing ceramic or ceramic composite for
9 the application of diesel particulate filters.

10

11 38. A use of a preceramic polymer to fabricate a lithium
12 aluminosilicate containing ceramic or ceramic composite
13 which is microwave susceptible.

14

15 39. A use of a preceramic polymer to fabricate a microwave
16 susceptible lithium aluminosilicate containing ceramic or
17 ceramic composite for the application of regenerative diesel
18 particulate filters.

- 1 ~~40.~~ A use of a preceramic polymer to fabricate a microwave
2 susceptible lithium aluminosilicate containing ceramic or
3 ceramic composite for the application of regenerative diesel
4 particulate filters composed of matted ceramic fibrils
5 shaped in a corrugated cylindrical geometry.
- 6 ~~41.~~ A use of a preceramic polymer to fabricate a microwave
7 susceptible lithium aluminosilicate containing ceramic or
8 ceramic composite for the application of regenerative diesel
9 particulate filters composed of matted ceramic fibrils
10 shaped in a conical geometry.
- 11
- 12 ~~42.~~ A use of a preceramic polymer to fabricate a lithium
13 aluminosilicate containing ceramic or ceramic composite for
14 the applications of radiant burners, thermal oxidizers of
15 volatile organic compounds, filters, and automotive
16 catalytic converters.
- 17
- 18 ~~43.~~ A use of a preceramic polymer to fabricate a silicon

1 nitride containing ceramic or ceramic composite for the
2 application of diesel particulate filters.

3

4 ~~44.~~ A use of a preceramic polymer to fabricate a silicon
5 nitride containing ceramic or ceramic composite which is
6 microwave susceptible.

7

8 ~~45.~~ A use of a preceramic polymer to fabricate a microwave
9 susceptible silicon nitride containing ceramic or ceramic
10 composite for the application of regenerative diesel
11 particulate filters.

12

13 ~~46.~~ A use of a preceramic polymer to fabricate a microwave
14 susceptible silicon nitride containing ceramic or ceramic
15 composite for the application of regenerative diesel
16 particulate filters composed of matted ceramic fibrils
17 shaped in a corrugated cylindrical geometry.

18

1 47. A use of a preceramic polymer to fabricate a microwave
2 susceptible silicon nitride containing ceramic or ceramic
3 composite for the application of regenerative diesel
4 particulate filters composed of matted ceramic fibrils
5 shaped in a conical geometry.

6
7 48. A use of a preceramic polymer to fabricate a silicon
8 nitride containing ceramic or ceramic composite for the
9 applications of radiant burners, thermal oxidizers of
10 volatile organic compounds, filters, and automotive
11 catalytic converters.

12
13 49. A process of forming a photo-curable pre-ceramic
14 polymer, poly(ethynyl)-carbosilane to silicon carbide
15 ceramic comprising the steps of:
16 a. reacting sodium acetylide with organo-chlorosilanes;
17 and
18 b. condensing (polymerizing) the resultant organo-

